





TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-33-744-8100

FAX 82-33-744-8866

: TAK-2018-065170 Report No

Receipt Date: 2018.04.19.

Representative : Bae Jin Woo

Test Completion Date: 2018.04.30.

Company name: BL Tech Co., Ltd.

Address : 84, Toegyenonggong-ro, Chuncheon-si, Gangwon-do, Korea(Rep.)

Sample name : PRAX Repair Tape

Test Results

		750000		Acres de la constante de la co
TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Durometer Hardness(Type D)	_	-	76	ASTM D2240-15

- Usage of Report: QUALITY CONTROL

- Note: 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 - 2. This test report shall be used only within the purpose of its defined usage and shall not be used fo public relation, advertisement and lawsuit.
 - 3. This test report is olny valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Jung yu seok

Prepared by Jung yu seok Tel: 02-2092-3704

2018.04.30

You Seok Reviewed by You Seok Tel: 1577-0091(ARS ①→④)

Korea Testing & Research Institute

President Bym, Jong-Rip



QR Code for forgery

Page: 1 of 1

문서본은 시험결과에 대한 참고용입니다.

전자문서본(Electronic Copy)

